

PANKASKIN

uncoated folding boxboard (UC2)

END USES


Recommended for skin packs and cartons requiring high porosity and brightness.

QUALITY PROPERTIES

Brightness
ISO 2470 Top ISO %
78 +/- 1

Moisture content
ISO 287 7,5 % +/-1,5 300...325 g/m²
8,0 % +/-1,5 350...400 g/m²
8,5 % +/-1,5 425...525 g/m²

Internal bond strength
TAPPI UM 403 Scott J/m²
> 110



Stora Enso Pankakoski Oy
 FIN-81750 PANKAKOSKI, FINLAND
 Telephone +358 2046 123
 Telefax +358 2046 27624
 Part of Stora Enso Ingerois Oy
 All sales handled by Ingerois Board Mill

Stora Enso Ingerois Oy
 Ingerois Board Mill
 FIN-46900 ANJALANKOSKI, FINLAND
 Telephone +358 2046 117,
 Telefax +358 2046 26140